

Our cliché plates respect the quality standards bellow. Quality controls are made by probing with certified measuring tools.
We are not responsible for inappropried storage or use of our plates.

STD : Standard steel, 10mm thick plates
CHR: 12% chrome steel, 10mm thick plates

	steel cliché polished surface	steel cliché lapped surface	Chrome steel cliché polished surface	Chrome steel cliché lapped surface	steel and chrome cliché 4 sides lapped	Cylinders with chrome	Ecoprint plate 0.3 - 0.5mm	Ecoprint plate with chrome	Recoprint plate lapped	Coating
Steel	ESU 1.2510	ESU 1.2510	ESU 1.2436	ESU 1.2436		ESU 1.2436	1,1274	SS716	1,1274	Dycophot G
Surface	brillant	mat	brillant	mat		brillant	brillant	mat	mat	
Roughness Ra	0.10 µ	0.40 µ	0.10 µ	0.40 µ		0.05 µ	0.1 µ	0.1 µ	0.30 µ	
Roughness Rmax	2 µ	4 µ	2 µ	4 µ		1 µ	2.5 µ	2.5 µ	3.5 µ	
Hardness	62 HRC ± 2	62 HRC ± 2	62 HRC ± 2	62 HRC ± 2		62 HRC ± 2	49 HRC ± 2	49 HRC ± 2	49 HRC ± 2	
Flatness	10 µ / 100mm	10 µ / 100mm	10 µ / 100mm	10 µ / 100mm			0.2% width	0.2% width	0.2% width	
Thickness	10mm +0.1-0.3	10mm +0.1-0.3	10mm +0.1-0.3	10mm +0.1-0.3	10mm +0.1-0.3		0.5mm ±0.05	0.5mm ±0.05	0.5mm ±0.05	
Width	+0/-0.3mm	+0/-0.3mm	+0/-0.3mm	+0/-0.3mm	+0/-0.1mm		± 0.3mm	± 0.3mm	± 0.3mm	
Lengh < 450 mm	+0/-0.3mm	+0/-0.3mm	+0/-0.3mm	+0/-0.3mm	+0/-0.1mm	± 0.2mm	± 0.3mm	± 0.3mm	± 0.3mm	
Lengh > 450 mm	+0/-0.7mm	+0/-0.7mm	+0/-0.7mm	+0/-0.7mm			± 0.5mm	± 0.5mm		
Lengh > 1000 mm							± 1 mm	± 1 mm		
Geometry	0.3mm	0.3mm	0.3mm	0.3mm	0.05mm	0.05mm	0.2mm	0.2mm	0.2mm	
Diameter						100mm ±0.02				
Coating thickness										5 µ ± 1